

# TECHNICAL DATA SHEET

## BONDAN AN42

Revision: 03.03.2021

Version: 1.001



### PRODUCT DESCRIPTION

BONDAN AN42 is a solvent-free, **medium strength**, anaerobic curing flange sealant. The sealant is well suited for all types of flanges (e.g. engine casings and gearboxes) as well as surface area applications such as pipe threads and connection pieces. In many applications BONDAN AN42 can be used to replace solid gaskets. Due to its medium strength disassembling is usually possible without damaging the components.

When cured, BONDAN AN42 exhibits a high dynamic fatigue strength and good long-term temperature behavior. The product protects against leaks caused by shocks and vibrations as well as unintentional unfastening of the components.

### TECHNICAL PROPERTIES

Color	brown
Chemical basis	Dimethacrylate ester
Viscosity at 25 °C	≈ 400 – 1000 mPa·s (Brookfield, sp. 3, 30 rpm)
Density at 25 °C (DIN EN 542)	1.1 g/cm <sup>3</sup>
Max. gap	0.25 mm or M36
Fixture time (rt, M10):	
Zinc-phosphated	< 20 min
Stainless steel	< 20 min
Zinc galvanized steel	< 20 min

The fixture time is especially influenced by the material surface, the gap and the curing temperature. In the case of passive surfaces and/or low temperatures, curing can be accelerated using the activator BONDAN AT91.

### PROPERTIES IN THE CURED STATE

Locking torque (ISO 10964)	
Breakaway	≈ 14 Nm
Prevailing	< breakaway torque
Compression shear strength (referring to ISO 10123)	≈ 12 N/mm <sup>2</sup>
Temperature range	-60°C/+150°C

### Chemical resistance (DIN 53287 – test method referring to DIN 54454)

Depicted is the relative strength in % after 1000 h exposure to the specific chemical

water/ethylene glycol (87 °C)	100 %
motor oil (MIL-L-46 152; 125 °C)	100 %
gasoline (rt)	95 %
brake fluid (rt)	100 %
ethanol (rt)	90 %
acetone (rt)	85 %

# TECHNICAL DATA SHEET

## BONDAN AN42

Revision: 03.03.2021

Version: 1.001



### DIRECTIONS FOR USE

- Please consult the safety data sheet before use.
- Clean, dry and grease-free surfaces ensure the maximum strength.
- Soiled surfaces must be cleaned (e.g. with BONDAN Cleaner or an appropriate solvent).
- Ensure sufficient flash-off time when cleaning parts.
- The curing time is especially influenced by the material pairing, curing temperature, gap and substrate surface.
- Dismantling and removal of adhesive residues can be facilitated by heating to 250 °C.
- This product is not suitable for application in an atmosphere consisting of pure oxygen or in highly oxidizing environments (e.g. chlorine).

### STORAGE

- 12 months at 8 to 21 °C in unopened packaging
- Do not store in the refrigerator

### PRODUCT LABELLING

See safety data sheet.

### PACKAGE UNITS

- For manual application 50 g, 250 g

All information provided is based on our extensive tests and practical experience. The data are given for information only. Drei Bond cannot assume responsibility for the results obtained by others which methods are not under our control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. Drei Bond disclaims all warranties expressed or implied, including warranties of fitness for a particular purpose, arising from sale or use of BONDAN products.